



PAVEMENT AGGREGATE QUALITY / DURABILITY REPORT

Client: Glendon Quarry Pty Ltd Client Address: PO Box 771, Glendon Road , Anakie Project: Glendon Quarry Compliance Testing Location: Glendon Road Rubyvale Supplied To: John Osbourne Area Description:	Report Number: 1692/R/10078-1 Project Number: 1692/P/318 Lot Number: Internal Test Request: 1692/T/3848 Client Reference/s: 5/03/18 Report Date / Page: 7/03/2018 Page 1 of 2
---	---

Sample Number 1692/S/22044 Sampling Method Tested As Received Date Sampled 5/03/2018 Specification Number 14mm Aggregate Material Source Glendon Quarry	Stockpile Lot No 14mm Sample No - - - Material Type 14mm Aggregate
--	---

Test Method	Sieve Size / Test Result	Test Date	Specification Minimum	Result	Specification Maximum	Specification Target [Diff]
Q103B	Particle Size Distribution (% passing)	06/03/2018				
	19.0mm		100	100	100	
	13.2mm		85	94	100	
	9.5mm		0	19	30	
	6.7mm		0	0.5	5	
	2.36mm		0	0.2	1	
Q202	Average Least Dimension (mm)	07/03/2018		8.4		
Q201	Flakiness Index (%)	07/03/2018		17		


Remarks

	<p style="text-align: center; font-size: small;">The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards. Accredited for compliance with ISO/IEC 17025 - Testing</p> <p>Accreditation Number: 1986 Corporate Site Number: 1692</p>	 Approved Signatory: Andrea Fleming Form ID: I03Rep Rev 1
--	--	--

PAVEMENT AGGREGATE QUALITY / DURABILITY REPORT



Client: Glendon Quarry Pty Ltd Client Address: PO Box 771, Glendon Road , Anakie Project: Glendon Quarry Compliance Testing Location: Glendon Road Rubyvale Supplied To: John Osbourne Area Description:	Report Number: 1692/R/10078-1 Project Number: 1692/P/318 Lot Number: Internal Test Request: 1692/T/3848 Client Reference/s: 5/03/18 Report Date / Page: 7/03/2018 Page 2 of 2
---	---

PARTICLE SIZE DISTRIBUTION GRAPH - 1692/S/22044



Method / Test	Test Details
Q103B / Washed State:	Unwashed
Q202 / Aggregate Median Size (mm):	10.88
Q201 / Drying Method:	Oven

Remarks

	<p style="text-align: center; font-size: small;">The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards. Accredited for compliance with ISO/IEC 17025 - Testing</p> <p>Accreditation Number: 1986 Corporate Site Number: 1692</p>	 Approved Signatory: Andrea Fleming Form ID: I03Rep Rev 1
---	--	--