


PARTICLE SIZE DISTRIBUTION REPORT



Client: Glendon Quarry Emerald Client Address: PO Box 771, Emerald Project: Glendon Quarry Material Investigation Location: Emerald Component: Area Description:	Report Number: 1699/R/1413-1 Project Number: 1699/P/5 Lot Number: n/a Report Date: 30/05/2013 Client Reference/s: E0911/869 Page Number: Page 1 of 1
---	---

Test Procedures: Q103A	
Sample Number: 1699/S/910 Sampling Method: Sampled by Client Date Sampled: 28/05/2013 Sampled By: Client Sampled Date Tested: 29/05/2013 Material Source: Glendon Quarry	Sample Location: Stockpile on Site Chainage: Offset: Remarks: Material Type: CBR 15 Material

AS Sieve (mm)	Specification Minimum	Percent Passing (%)	Specification Maximum
53.0		100	
37.5		97	
19.0		48	
9.5		27	
4.75		14	
2.36	20.0	6.1	70.0
0.425		3.6	
0.075	0.0	2.5	25.0
Grading Result Analysis			
0.075/0.425 Ratio		0.69	
D10 (mm)		3.60	
D60 (mm)		23.51	
UC (D60/D10)		6.53	



Remarks: 3994/11	
-------------------------	--

	<p>The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards. Accredited for compliance with ISO/IEC 17025</p> <p>Laboratory Accreditation No.: 1699</p>	 <p>Approved Signatory: Donna Marr Form ID: W9Rep Rev 1</p>
---	--	---